

**LZR Fit as of 8/1/2018**

Estimated amount of thinning from forming heads											
head thickness	<b>2:1 Ellip</b>										
Head Ø	10ga	7ga	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"	
18			0.035								
24			0.035								
36							0.070				
48			0.045								
60							0.080	0.080	0.090	0.130	
72											
84			0.050								
96			0.060							0.105	
108											
120			0.040		0.063		0.068	0.070	0.110	0.140	
144											

Estimated amount of thinning from forming heads										
head thickness	<b>80:10 &amp; ASME High Crown</b>									
Head Ø	10ga	7ga	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"
18										
24										
36										
48										
60										
72			0.050							
84					0.063		0.080			
96								0.090		
108										0.155
120										
144										

Estimated amount of thinning from forming heads											
head thickness	<b>ASME &amp; STD F&amp;D</b>										
Head Ø	10ga	7ga	3/16"	1/4"	5/16"	3/8"	1/2"	5/8"	3/4"	1"	
18											
24			0.035								
36								0.040			
48											
60											
72											
84									0.065	0.115	
96											
108			0.045					0.050			
120											
144											
150									0.090		
156											

For other head types please contact:

LZR FIT Customer Care | 715.453.5326 | [info@lzrfit.com](mailto:info@lzrfit.com)

Phone: 715-453-5326

Email: [info@lzrfit.com](mailto:info@lzrfit.com)

Website: [www.lzrfit.com](http://www.lzrfit.com)